

A

Transmittal Letter for Patent Application

Applicants: Brian D. Morrison, Ingrid Cole, and Justin A. Mehaffy

Title: LOW APPLICATION TEMPERATURE HOT MELT ADHESIVE

Transmitted herewith for filing are:

- ☒ Application and Claims  
☒ Sheets of Drawing  
☒ Declaration or Oath and Power of Attorney Executed by Inventors  
☒ Information Disclosure Statement  
☒ Form PTO-1449  
☒ References  
☒ Certified Copy of \_\_\_\_\_ Application  
☒ Assignment to National Starch and Chemical Investment Holding Corporation

11/12/99  
6590 U.S. PTO


JCS75 U.S. PTO  
09/13/95  
5562/11

CLAIMS AS FILED

| FOR                          | NUMBER FILED | NUMBER EXTRA | RATE     | FEE        |
|------------------------------|--------------|--------------|----------|------------|
| TOTAL CLAIMS                 | 9            |              |          | -          |
| INDEPENDENT CLAIMS           | 2            |              |          | -          |
| MULTIPLE DEPENDENT CLAIM FEE | 1            |              | \$260.00 | \$260.00   |
| BASIC FEE                    |              |              |          | \$760.00   |
| TOTAL FILING FEE             |              |              |          | \$1,020.00 |

- ☒ Please charge Deposit Account No. 14-0455 in the amount of \$1,020.00.  
A duplicate copy of this Sheet is enclosed.
- ☒ The Commissioner is hereby authorized to charge any additional fees which may be required at any time during the prosecution of this application without specific authorization, or credit any overpayment to Deposit Account No. 14-0455. A duplicate copy of this sheet is enclosed.

November 12, 1999  
Date

  
Ellen T. Dec, Reg. No. 26,863  
Attorney for Applicants  
Tel. No. (908) 685-5130


National Starch and Chemical Company  
P.O. Box 6500  
Bridgewater, New Jersey 08807-0500

Express Mail Certification

Date of Deposit:

Mailing Label Number:

I certify that I am depositing the above identified papers pursuant to 37 CFR §1.10 with the United States Postal Service as "Express Mail - Post Office to Addressee" on the above stated date under the above stated mailing label number in an envelope addressed to the Assistant Commissioner for Patents, Washington, D.C. 20231.

  
Fred A. Catalano

11/12/99  
JC630 U.S. PTO

Express Mail Certification

Date of Deposit: November 12, 1999  
Mailing Label Number: EM404736834US

I certify that I am depositing this paper pursuant to 37 CFR §1.10 with the United States Postal Service as "Express Mail - Post Office to Addressee" on the above stated date under the above stated mailing label number in an envelope addressed to the Assistant Commissioner for Patents, Washington, DC 20231.

*Fred A. Catalano III*  
Fred A. Catalano III

Brian D. Morrison  
Ingrid Cole  
Justin A. Mehaffy

Patent No. 1843

5 LOW APPLICATION TEMPERATURE HOT MELT ADHESIVE

BACKGROUND OF THE INVENTION

Hot-melt adhesives, are materials which are applied to a substrate when molten and cooled to harden the adhesive layer, and are widely used for industrial applications.

- 10 Most commercially available hot-melt adhesives require temperatures of 350°F or greater to ensure complete melting of all the components and also to achieve a satisfactory application viscosity. The need for such elevated temperatures is not without problems. The high temperatures increase the operators risks with respect both to burns and to inhalation of residual volatiles. In addition, the high temperatures
- 15 require more energy, placing greater demands on the manufacturing facility.

- Adhesive formulations which can be applied at temperatures below 300°F may be prepared using low molecular weight components or by incorporating a high wax content. Although these formulations achieve low application viscosity, there is a resulting loss of adhesive properties. Therefore, to improve adhesion, softer or more
- 20 amorphous components are added. However, these amorphous components reduce the effective heat resistance, particularly under cantilever stressed bonds subjected to high temperatures for an extended duration.

- Accordingly it would be desirable to have an adhesive which has good bond strength with exceptional heat resistance and application viscosity, even if prepared with
- 25 low molecular weight components for application at low temperatures.

## SUMMARY OF THE INVENTION

We have now found hot-melt adhesives prepared from

- a) about 5 to about 60 weight percent ethylene vinyl acetate having a vinyl acetate content of about 30 to about 50 weight percent and a melt index of about 700 to about 4,000 dg/min;
- b) about 5 to about 60 weight percent of a tackifier; and
- c) about 15 to about 55 weight percent wax with a melting point of about 125°F to about 180°F.

10 The hot-melt adhesive compositions of the present invention can be applied at temperatures of 200°F to 300°F yet still provide exceptional heat resistance despite using low molecular weight components which would conventionally be thought to produce poor heat and cold resistance.

15 Accordingly, the hot-melt adhesives of the present invention find use in case and carton sealing operations. Corrugated cases are often subjected to high stresses and adverse environmental conditions during shipping. The hot-melt adhesives of the present invention meet the rigorous requirements for this and other applications.

## 20 DETAILED DESCRIPTION OF THE INVENTION

The present invention is directed to hot-melt adhesive compositions which can be applied at temperatures between 200°F to 300°F yet still provide exceptional heat resistance and good cold adhesion despite using low molecular weight components.

25 The ethylene vinyl acetate copolymers (EVA) useful herein are those containing about 30 weight percent to about 50 weight percent vinyl acetate and having a melt index of about 700 dg/min to about 4,000 dg/min. The preferred copolymers are available from EXXON under the designation Escorene MV01040 and comprise approximately 40 weight percent vinyl acetate and have a melt index of about 1,000 dg/min. The amount of the copolymer present in the hot-melt adhesive 30 varies from about 5 to 60 weight percent by weight, preferably about 35 to about 45 weight percent by weight.

Tackifiers useful in the present invention include terpene, terpene phenolic, modified terpene, and combinations thereof. Terpene phenolic tackifiers also include the hydrogenated derivatives of phenolic modified terpene resins, for example, as the resin product resulting from the condensation, in an acidic medium, of a bicyclic terpene and a phenol. Nirez 2040, a phenolic modified terpene having a Ring and Ball softening point about 125°C and available from Arizona Chemicals, is the most preferred.

For use herein, it is also important that the tackifiers have a Ring and Ball softening point less than about 130°C, preferably about 125°C.

Tackifiers are utilized in amounts of about 5 weight percent to about 60 weight percent, by weight of the hot-melt adhesive composition. The present invention contemplates that the hot-melt adhesive composition of the present invention comprise one or more of the above tackifiers.

The compositions of this invention may optionally contain at least one additional tackifier selected from the group consisting of rosin, rosin derivatives, rosin ester, aliphatic hydrocarbons, aromatic hydrocarbons, aromatically modified aliphatic hydrocarbons and mixtures thereof. Examples of rosin ester tackifiers include both natural and modified rosins such as gum rosin, wood rosin, tall-oil rosin, distilled rosin, hydrogenated rosin, dimerized rosin, polymerized rosin, as well as the glycerol and pentaerythritol esters of natural and modified rosins, such as, for example, the glycerol ester of pale wood rosin, the glycerol ester of hydrogenated rosin, the glycerol ester of polymerized rosin, the pentaerythritol ester of hydrogenated rosin, the phenolic-modified pentaerythritol ester of rosin, and combinations thereof. Glycerol rosin ester is the most preferred rosin ester.

Representative additional tackifiers include NIREZ V-2040 and NIREZ 300 from Arizona Chemical Company, and DERTOPHENE T 105 from DRT. Other commercially available tackifiers include SYLVATAC 100, ZONATAC and ZONESTER from Arizona Chemical Company, PERMALYN from Hercules, UNITAC Union Carbide and NOVARES from Georgia Pacific.

Waxes suitable for use in the present invention are paraffin waxes having melting points in the range of about 125 to 175°F, such as, for example, PACEMAKER

from Citgo, and R-2540 from Moore and Munger; and low melting point synthetic waxes (i.e. Fischer-Tropsch waxes) having a melting point of less than about 180°F. The most preferred wax is paraffin wax with a melting point of about 150°F. The wax component is utilized at levels of about 15 weight percent to about 55 weight percent, by weight of the hot-melt adhesive.

The hot-melt adhesives of the present invention may also contain a stabilizer or antioxidant. Among the applicable stabilizers or antioxidants included herein are high molecular weight hindered phenols and multifunctional phenols such as sulfur and phosphorous-containing phenol. Hindered phenols are well known to those skilled in the art and may be characterized as phenolic compounds which also contain sterically bulky radicals in close proximity to the phenolic hydroxyl group thereof. In particular, tertiary butyl groups generally are substituted onto the benzene ring in at least one of the ortho positions relative to the phenolic hydroxyl group. The presence of these sterically bulky substituted radicals in the vicinity of the hydroxyl group serves to retard its stretching frequency, and correspondingly, its reactivity; this hindrance thus providing the phenolic compound with its stabilizing properties. Representative hindered phenols include; 1,3,5-trimethyl-2,4,6-tris-(3,5-di-tert-butyl-4-hydroxybenzyl)-benzene; pentaerythrityl tetrakis-3(3,5-di-tert-butyl-4-hydroxyphenyl)-propionate; n-octadecyl-3(3,5-di-tert-butyl-4-hydroxyphenyl)-propionate; 4,4'-methylenebis (2,6-tert-butyl-phenol); 4,4'-thiobis (6-tert-butyl-o-cresol); 2,6-di-tertbutylphenol; 6-(4-hydroxyphenoxy)-2,4-bis(n-octyl-thio)-1,3,5 triazine; di-n-octylthio)ethyl 3,5-di-tert-butyl-4-hydroxy-benzoate; and sorbitol hexa[3-(3,5-di-tert-butyl-4-hydroxy-phenyl)-propionate].

The performance of these antioxidants or stabilizers may further be enhanced by utilizing, in conjunction therewith, known synergists such as, for example, thiodipropionate esters and phosphites. Distearylthiodipropionate is particularly useful. These, if used, are generally present in amounts of about 0.1 to 1.5 weight percent, preferably 0.25 to 1.0 weight percent.

Depending on the contemplated end uses of the hot-melt adhesives, other additives such as plasticizers, pigments and dyestuffs conventionally added to hot-melt adhesives may be included. In addition, small amounts of additional tackifiers

and/or waxes such as microcrystalline waxes, hydrogenated castor oil and vinyl acetate modified synthetic waxes may also be incorporated in minor amounts, i.e., up to about 10 weight percent by weight, into the formulations of the present invention.

5 A preferred embodiment of the present invention is directed to a hot-melt adhesive composition comprising:

- a) about 35 weight percent ethylene vinyl acetate with about 40 weight percent vinyl acetate and having a melt index of at about 1,000;
- b) about 30 weight percent of a tackifier selected from the group consisting of terpene, terpene phenolic, modified terpenes, and combinations thereof;
- 10 c) about 5 weight percent of at least one additional tackifier selected from the group consisting of hydrogenated glycerol, pentaerythritol, and combinations thereof; and
- d) about 30 weight percent wax with a melting point of about 150°F.

15 The hot-melt adhesive compositions of the present invention are prepared by blending the components in the melt at a temperature of about 135°C until a substantially homogeneous blend is obtained, approximately two hours. Various methods of blending are known in the art and any method that produces a homogeneous blend is satisfactory.

20 The resulting hot-melt adhesives are characterized by a viscosity less than about 5,000 cps at 250°F. They may be applied at temperatures of 200 to 300°F to provide superior adhesive bonds even when exposed to a wide variety of temperature conditions. The hot-melt adhesives possess excellent heat stability as characterized by the 72 hour 275°F thermal stability test, which shows no signs of char, skinning, gel formation or phase separation. In addition, a bond formed by two  
25 pieces of corrugated case substrate held together by a ½" by 2" compressed bead can maintain a cantilever stress load of 2 to 2.5 psi for 24 hours at temperatures at or above 115°F. The resulting hot-melt adhesive is also characterized by showing good adhesion properties down to about -30°F.

30 As such the hot-melt adhesives find particular use as case, carton and tray forming and as sealing adhesives, for example, in the packaging of frozen or refrigerated food products. The hot-melt adhesives of the present invention are

particularly useful for use in the packaging, converting, bookbinding and nonwoven markets, especially for primary case and carton sealing and for use in the cigarette industry.

5

#### EXAMPLES

In the following examples, which are provided for illustrative purposes only, all parts are by weight and all temperatures in degrees Celsius unless otherwise noted.

10 In the examples, all hot-melt adhesive formulations were prepared in single blade mixer heated to 135°C by blending the components until homogeneous.

The hot-melt adhesives were then subjected to various tests simulating the properties needed for successful commercial applications.

Melt viscosities of the hot-melt adhesives were determined on a Brookfield Model RVT Thermosel viscometer using a number 27 spindle.

15 Adhesion at various temperatures, as noted, was determined by applying a 1/2 inch wide bead of hot-melt adhesive widthwise to a 1 inch by 2 inch piece of substrate (comprising polyethylene-coated SBS) and immediately bringing a second piece of substrate into contact. The bond is aged at each temperature for 24 hours. The bonds were separated by hand and a determination made as to the type of  
20 failure and the presence or absence of fiber tear (FT) was noted. "Full" as used in the examples herein refers to 95 to 100% fiber tear. "Partial" refers to 25 to 95% fiber tear. "Slight" refers to 1 to 25% fiber tear; and "No" refers to 0 to 1% fiber tear.

Heat stress was measured by forming a composite construction of adhesive (2 X ½" compressed) between two pieces of corrugated of specific dimensions. The  
25 adhesive bead forming this composite is then placed under approximately 2 pounds of cantilever stress for 24 hours at elevated temperatures. The maximum temperature at which this construction remains in tact for at least 24 hours is then noted.

Clarity was determined by heating 100 g of the adhesive blends to 135°C  
30 (275°F) in a 4 oz glass jar. A thermometer was placed in the jar and its visibility assessed visually as follows. If the thermometer remained visible as it was moved

from the front to the back of the jar the product was designated "Clear"; if it remained visible only until the thermometer was moved to the center of the jar it was designated "Moderately Hazy"; and if it was visible only at the front of the jar it was designated "Hazy".

- 5 These measures of clarity provide an indication of a hot melt's overall compatibility, i.e., the compatibility of the individual ingredients with each other. Products that are clear reflect an overall compatible product. Systems which are hazy at their application temperature exhibit a micro separation changing the refraction index of the molten adhesive.

- 10 The following materials were used to prepare a series of adhesives in accordance with the present invention: Irganox 1010 (available from Ciba Geigy); Nirez 2040 (available from Arizona Chemical Co.); Sylvatic 40N (available from Arizona Chemical Co.); Unitac R100 (available from Union Camp); Kristalex 3100 (available from Hercules Co.)

15

|                                 | Example<br>1             | Example<br>2   | Example<br>3   | Example 4      | Example 5                    |
|---------------------------------|--------------------------|----------------|----------------|----------------|------------------------------|
| Irganox 1010                    | 0.5                      | 0.5            | 0.5            | 0.5            | 0.5                          |
| 150°F SP Wax                    | 30                       | —              | —              | —              | 10                           |
| 40% VA / 1000MI EVA             | 35                       | 60             | 70             | 90             | 50                           |
| Nirez 2040 125°C SP             | 35                       | 40             | 30             | 10             | 40                           |
| Viscosity @ 275°F               | 1,400                    | 26,950         | 29,250         | 34,200         | 9,675                        |
| Adhesion @ R T<br>40°F<br>-30°F | Full<br>Partial<br>Full  | NA<br>NA<br>NA | NA<br>NA<br>NA | NA<br>NA<br>NA | Slight<br>Partial<br>Partial |
| Kanebo Set Time<br>W/1sec OT    | ~ 1.7 sec.<br>~ 3.5 sec. | NA<br>NA       | NA<br>NA       | NA<br>NA       | ~ 2.5 sec.<br>~ 4.5 sec.     |
| Open Time w/ 10 sec<br>ST       | ~ 3.0 sec.               | NA             | NA             | NA             | ~ 6.0 sec.                   |
| Clarity                         | Clear                    | Clear          | Clear          | Clear          | Clear                        |
| Open Time w/ 10 sec<br>ST       | ~ 3.0 sec.               | —              | —              | —              | —                            |



Example 1 is formulated according to the present invention and shows very good adhesion and viscosity properties.

Comparative Example 2 contains EVA and tackifier but not wax according to the present invention and has unacceptably high viscosity;

Comparative Examples 3 and 4 contain tackifier but neither wax nor EVA according to the present invention and again have unacceptably high viscosities.

Comparative Example 5 contains EVA and tackifier according to the present invention, but does not contain the claimed amount of wax and shows poor adhesion properties.

|                                    | <u>Example 7</u>        | <u>Example 8</u> | <u>Example 9</u>           | <u>Example 10</u>          |
|------------------------------------|-------------------------|------------------|----------------------------|----------------------------|
| Irganox 1010                       | 0.5                     | 0.5              | 0.5                        | 0.5                        |
| 150°F SP Wax                       | 30                      | 30               | 35                         | 35                         |
| 33% VA / 400MI EVA                 | 35                      | —                | 30                         | 27                         |
| 40% VA / 50MI EVA                  | —                       | 35               | —                          | —                          |
| 40% VA / 1000MI EVA                | —                       | —                | —                          | —                          |
| Nirez 2040 125°C SP                | 35                      | 35               | 35                         | 38                         |
| Viscosity @ 275°F                  | 2,330                   | 9,175            | 1,455                      | 1,100                      |
| Adhesion @<br>R T<br>40°F<br>-30°F | Partial<br>None<br>Full | NA<br>NA<br>NA   | Partial<br>None<br>Partial | Partial<br>None<br>Partial |
| Clarity                            | Clear                   | Hazy             | Moderately<br>Hazy         | Moderately<br>Hazy         |
| Open Time w/ 10 sec ST             | NA                      | NA               | NA                         | ~ 6.0 sec.                 |

Comparative Examples 7 to 9 contain EVA having melt indexes outside the scope of this invention. It can be seen from these examples that the melt index of the EVA component according to this invention is necessary to provide good viscosity, clarity and adhesion.

|  | Example 11            | Example 12           | Example 13     | Example 14        |
|--|-----------------------|----------------------|----------------|-------------------|
| Irganox 1010                                 | 0.5                   | 0.5                  | 0.5            | 0.5               |
| 150°F SP Wax                                 | 30                    | 30                   | 30             | 30                |
| 40% VA / 1,000MI EVA                         | 35                    | —                    | —              | 35                |
| Nirez 2040 125°C SP                          | 30                    | 30                   | 30             | —                 |
| 40°C SP Sylvatac 40N Rosin Ester             | 5                     | 5                    | 5              | 5                 |
| 28% VA / 900MI EVA                           | —                     | —                    | —              | —                 |
| 28% VA / 2,500 MI EVA                        | —                     | 35                   | —              | —                 |
| 33% BA / 900MI EnBA                          | —                     | —                    | 35             | —                 |
| 100°C SP Unitac R100 Rosin Ester             | —                     | —                    | —              | 30                |
| 100°C SP Kristalex 3100 Alpha-methyl styrene | —                     | —                    | —              | —                 |
| Viscosity @ 275°F                            | 1,115                 | 555                  | 1,055          | 710               |
| Adhesion @ R T 40°F -30°F                    | Full Partial Partial  | Partial Partial None | Full None None | Partial None None |
| KANEBO Set Time W/1 sec OT                   | Partial 1.75 Full 3.5 | 1.7 4.2              | 1.2 3.0        | 2.7 6.2           |
| Open Time w/ 10 sec ST                       | 3.0                   | 2.0                  | 3.0            | 1.5               |
| Heat Stress Pass Temp.                       | 115°F                 | 105°F                | 110°F          | 105°F             |

Example 11 represents a preferred formulation according to this invention and has good viscosity, adhesion and heat stress properties.

- 5 Comparative Example 12 contains EVA copolymer having a VA content less than that stipulated in this invention and Comparative Example 13 is formulated using EnBA copolymer, these formulations show poor heat resistance and adhesion. Comparative Examples 14 and 15 do not contain the required tackifier and as a result they show poor adhesion, slow set speed and/or low heat resistance.

|   | Example 15           | Example 16              |
|---|----------------------|-------------------------|
| Irganox 1010                                    | 0.5                  | 0.5                     |
| 150°F SP Wax                                    | 30                   | 30                      |
| 40% VA / 1,000MI EVA                            | 35                   | —                       |
| Nirez 2040 125°C SP                             | —                    | 30                      |
| 40°C SP Sylvatac 40N<br>Rosin Ester             | 5                    | 5                       |
| 28% VA / 900MI EVA                              | —                    | 35                      |
| 28% VA / 2,500 MI EVA                           | —                    | —                       |
| 33% BA / 900MI EnBA                             | —                    | —                       |
| 100°C SP Unitac R100<br>Rosin Ester             | —                    | —                       |
| 100°C SP Kristalex 3100<br>Alpha-methyl styrene | 30                   | —                       |
| Viscosity @ 275°F                               | 735                  | 1,190                   |
| Adhesion @ R T<br>40°F<br>-30°F                 | None<br>None<br>None | Full<br>Partial<br>None |
| KANEBO Set Time W/1<br>sec OT                   | 2.5<br>6.0           | 1.5<br>2.5              |
| Partial<br>Full                                 |                      |                         |
| Open Time w/ 10 sec ST                          | 1.5                  | 3.0                     |
| Heat Stress Pass Temp.                          | 120°F                | 105°F                   |

- Comparative Example 16 contains EVA copolymer whose vinyl acetate content falls outside the claims of the present invention. This formulations show poor heat resistance and adhesion.

WE CLAIM:

1. A hot melt adhesive composition comprising:
  - a) about 5 weight percent to about 60 weight percent ethylene vinyl acetate having a vinyl acetate content of about 30 weight percent to 50 weight percent and a melt index of about 700 to 4,000 dg/min;
  - 5 b) about 5 weight percent to about 60 weight percent of a tackifier; and
  - c) about 15 weight percent to about 55 weight percent wax with a melting point of about 125°F to 180°F.
- 10 2. An adhesive according to Claim 1 wherein the tackifier has a Ring and Ball softening point of less than about 130°C.
- 15 3. An adhesive according to Claim 2 wherein the tackifier is selected from the group consisting of terpene, terpene phenolic, modified terpene, and combinations thereof.
- 20 4. An adhesive according to Claim 1 wherein the ethylene vinyl acetate copolymer comprises about 35 weight percent to about 45 weight percent vinyl acetate.
5. An adhesive according to Claim 1 wherein the ethylene vinyl acetate copolymer comprises about 40 weight percent vinyl acetate.
- 25 6. An adhesive according to Claim 1 wherein the wax is paraffin wax or low melting point synthetic wax.
- 30 7. An adhesive according to Claim 1 additionally comprising up to about 5 weight percent of at least one additional tackifier selected from the group consisting of rosin, rosin derivatives, rosin ester, aliphatic hydrocarbons, aromatic hydrocarbons, aromatically modified aliphatic hydrocarbons and mixtures thereof.

8. An adhesive composition comprising:

a) about 35 weight percent ethylene vinyl acetate with about 40 weight percent vinyl acetate and having a melt index of at about 1,000;

5 b) about 30 weight percent of a tackifier selected from the group consisting of terpene, terpene phenolic, modified terpenes, and combinations thereof;

c) about 5 weight percent of at least one additional tackifier selected from the group consisting of hydrogenated glycerol, pentaerythritol, and combinations thereof;

10 d) about 30 weight percent wax with a melting point of about 150°F.

9. A carton, case or tray formed utilizing the adhesive composition of Claims 1, 7 or 8.

### ABSTRACT OF THE DISCLOSURE

A low application temperature hot met adhesive composition and its use in carton, case or tray formation comprising from about 5 to about 60 weight percent ethylene vinyl acetate with about 30 to about 50 weight percent VA content and having a melt index of about 700 to about 4,000 dg/min; a tackifier; and wax with a melting point of about 125 to about 180°F.

DECLARATION FOR PATENT APPLICATION

As a below named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated below next to my name.

I believe that I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled LOW APPLICATION TEMPERATURE HOT MELT ADHESIVE the specification of which

(check one)

☒ is attached hereto

☐ was filed on \_\_\_\_\_ as

Application Serial No. \_\_\_\_\_ and was amended on \_\_\_\_\_ (if applicable).

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose information which is material to the patentability of this application in accordance with Title 37, Code of Federal Regulations, §1.56(a).

I hereby claim foreign priority benefits under Title 35, United States Code, §119 of any foreign application(s) for patent or inventor's certificate listed below and have also identified below any foreign application for patent or inventor's certificate having a filing date before that of the application on which priority is claimed:

Prior Foreign Application(s)

Priority Claimed

| (Number) | (Country) | (Day/Month/Year Filed) | Yes   | No    |
|----------|-----------|------------------------|-------|-------|
| _____    | _____     | _____                  | _____ | _____ |
| (Number) | (Country) | (Day/Month/Year Filed) | Yes   | No    |
| _____    | _____     | _____                  | _____ | _____ |
| (Number) | (Country) | (Day/Month/Year Filed) | Yes   | No    |
| _____    | _____     | _____                  | _____ | _____ |

I hereby claim the benefit under Title 35, United States Code, §120 of any United States application(s) listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States application in the manner provided by the first paragraph of Title 35, United States Code, §112, I acknowledge the duty to disclose material information as defined in Title 37, Code of Federal Regulations, §1.56(a), which occurred between the filing date of the prior application and the national or PCT international filing date of this application:

| (Application Serial No.) | (Filing Date) | (Status-patented, pending, abandoned) |
|--------------------------|---------------|---------------------------------------|
| _____                    | _____         | _____                                 |

| (Application Serial No.) | (Filing Date) | (Status-patented, pending, abandoned) |
|--------------------------|---------------|---------------------------------------|
| _____                    | _____         | _____                                 |

I hereby appoint the following attorney(s) and/or agent(s) to prosecute this application and to transact all business in the Patent and Trademark Office connected herewith:

Ellen T. Dec. Reg. No. 26,863; Laurelee A. Duncan, Reg. No. 44,096; Jane E. Gennaro, Reg. No. 34,884; Karen G. Kaiser, Reg. No. 33,506;  
John D. Thallmer, Reg. No. 34,940

Address all telephone calls to Ellen T. Dec at telephone no. 908-685-5130

Address all correspondence to Ellen T. Dec, General Counsel  
National Starch and Chemical Company  
Box 6500  
Bridgewater, New Jersey 08807-0500

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

Full name of sole or first inventor Brian D. Morrison

Inventor's Signature Brian D. Morrison

Date 11/12/99

Residence 7 Galloping Hill Road, Lebanon, NJ 08833

Citizenship United States

Post Office Address 7 Galloping Hill Road, Lebanon, NJ 08833

Full name of second joint inventor, if any Ingrid Cole

Second Inventor's Signature Ingrid Cole

Date 11/12/99

Residence 17 E. Spring Street, Somerville, NJ 08876

Citizenship United States

Post Office Address 17 E. Spring Street, Somerville, NJ 08876

Third Inventor's Signature \_\_\_\_\_

Date 11/12/99

Residence

1 Ridge Road, Flemington, NJ 08822

## Citizenship

United States

Post Office Address

1 Ridge Road, Flemington, NJ 08822

| Year | 1997 | 1998 | 1999 | 2000 | 2001 | 2002 | 2003 | 2004 | 2005 | 2006 | 2007 | 2008 | 2009 | 2010 | 2011 | 2012 | 2013 | 2014 | 2015 | 2016 | 2017 | 2018 | 2019 | 2020 | 2021 | 2022 | 2023 | 2024 | 2025 | 2026 | 2027 | 2028 | 2029 | 2030 | 2031 | 2032 | 2033 | 2034 | 2035 | 2036 | 2037 | 2038 | 2039 | 2040 | 2041 | 2042 | 2043 | 2044 | 2045 | 2046 | 2047 | 2048 | 2049 | 2050 | 2051 | 2052 | 2053 | 2054 | 2055 | 2056 | 2057 | 2058 | 2059 | 2060 | 2061 | 2062 | 2063 | 2064 | 2065 | 2066 | 2067 | 2068 | 2069 | 2070 | 2071 | 2072 | 2073 | 2074 | 2075 | 2076 | 2077 | 2078 | 2079 | 2080 | 2081 | 2082 | 2083 | 2084 | 2085 | 2086 | 2087 | 2088 | 2089 | 2090 | 2091 | 2092 | 2093 | 2094 | 2095 | 2096 | 2097 | 2098 | 2099 | 2100 |
|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|
| 1997 | 1998 | 1999 | 2000 | 2001 | 2002 | 2003 | 2004 | 2005 | 2006 | 2007 | 2008 | 2009 | 2010 | 2011 | 2012 | 2013 | 2014 | 2015 | 2016 | 2017 | 2018 | 2019 | 2020 | 2021 | 2022 | 2023 | 2024 | 2025 | 2026 | 2027 | 2028 | 2029 | 2030 | 2031 | 2032 | 2033 | 2034 | 2035 | 2036 | 2037 | 2038 | 2039 | 2040 | 2041 | 2042 | 2043 | 2044 | 2045 | 2046 | 2047 | 2048 | 2049 | 2050 | 2051 | 2052 | 2053 | 2054 | 2055 | 2056 | 2057 | 2058 | 2059 | 2060 | 2061 | 2062 | 2063 | 2064 | 2065 | 2066 | 2067 | 2068 | 2069 | 2070 | 2071 | 2072 | 2073 | 2074 | 2075 | 2076 | 2077 | 2078 | 2079 | 2080 | 2081 | 2082 | 2083 | 2084 | 2085 | 2086 | 2087 | 2088 | 2089 | 2090 | 2091 | 2092 | 2093 | 2094 | 2095 | 2096 | 2097 | 2098 | 2099 | 2100 |      |